

Halar 901 ECTFE

High Viscosity - Extrusion

H
A
L
A
R
®

Typical Physical Properties

Typical Properties	Test Method	US Unit	SI Unit
Physical Properties			
Density @ 23°C/73°F	ASTM D792	lb/ft ³	105 g/cm ³
Water Absorption	ASTM D570	%	<0.1
Melt Flow Index @ 275°C, 2.16 kg	ASTM D1238	g/10 min	1
Mechanical Properties			
Tensile	ASTM D638		
Tensile Yield Strength	23°C/73°F 2in/min (50mm/min)	psi	4300 MPa
Tensile Break Strength		psi	7800 MPa
Elongation at Yield		%	5
Elongation at Break		%	250
Tensile Modulus		psi	240,000 MPa
Flexural	ASTM D790		
Flexural Strength	23°C/73°F 0.1in/min (2.5mm/min)	psi	6800 MPa
Flexural Modulus		psi	245,000 MPa
Impact	ASTM D256		
Notched Izod Strength, 23°C/73°F	0.125 in (3.2 mm)	ft.lbf/in	No Break J/m
Notched Izod Strength, -40°C/-40°F		ft.lbf/in	2.0 J/m
Hardness, Shore D	ASTM D2240		75
Hardness, Rockwell R	ASTM D785		90
Abrasion Resistance, CS 17 (0.5kg)	Taber		mg/1000 rev
Friction Coefficient	ASTM D1894		
Static			0.2
Dynamic			0.2
Thermal Properties			
Melting Point	DSC	°F	468 °C
Heat of Fusion		BTU/lb	18 J/g
Crystallization Point		°F	432 °C
Crystallization Heat		BTU/lb	17 J/g
Specific Heat @ 23°C/73°F		BTU/lb-°F	0.23 J/g.K

For information contact your Solvay Solexis representative or:

Europe

Solvay Solexis S.p.A. (Italy)

Tel: +39-02-3835-1

Fax: +39-02-3835-2129

Email: solvaysolexis.ita@solvay.com

North America

Solvay Solexis, Inc.

Tel: +1-856-853-8119

Fax: +1-856-853-6405

Email: solvaysolexisinfo@solvay.com

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Solexis, Inc. nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes.

Trademarks and/or other Solvay Solexis, Inc. products referenced herein are either trademarks or registered trademarks of Solvay Solexis, Inc. or its affiliates.

Copyright 2003, Solvay Solexis, Inc. All Rights Reserved.

Halar 901 ECTFE

High Viscosity - Extrusion

Halar®

Typical Physical Properties

Typical Properties	Test Method	US Unit		SI Unit	
Thermal Properties (cont'd)					
DTUL, 66 psi (0.46 MPa)	ASTM D648	°F	195	°C	90
DTUL, 264 psi (1.82 MPa)	ASTM D648	°F	150	°C	65
Glass Transition Temperature (T _g)	DMA	°F	185	°C	85
Brittleness Temperature	ASTM D746A	°F	<-105	°C	<-76
Mold Shrinkage	ASTM 955	%	2.5		
Thermal Stability, 1% Mass Loss, N ₂	TGA	°F	760	°C	405
Linear Thermal Exp. Coefficient	ASTM D696	10 ⁻⁶ /°F	56	10 ⁻⁶ /K	100
Thermal Conductivity @ 40°C/104°F	ASTM C177	BTU- in/h-ft ² -°F	1.05	W/m.K	0.15
Electrical Properties					
Volume Resistivity @ 23°C, 50% RH	ASTM D257	ohm- in.	1.4 x 10 ¹⁶	ohm.cm	5.5 x 10 ¹⁶
Dielectric Strength @ 23°C/73°F @ 3.2 mm thickness	ASTM D149	V/mil	350	kV/mm	14
			2.57		
Dielectric Constant, 23°C @ 10 ⁶ Hz					
Fire Resistance					
UL-94 Flammability Test	UL-94	Class	V-0		
Limiting Oxygen Index	ASTM D2863	%	52		

For information contact your Solvay Solexis representative or:

Europe
Solvay Solexis S.p.A. (Italy)
Tel: +39-02-3835-1
Fax: +39-02-3835-2129
Email: solvaysolexis.ita@solvay.com

North America
Solvay Solexis, Inc.
Tel: +1-856-853-8119
Fax: +1-856-853-6405
Email: solvaysolexisinfo@solvay.com

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Solexis, Inc. nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes.

Trademarks and/or other Solvay Solexis, Inc. products referenced herein are either trademarks or registered trademarks of Solvay Solexis, Inc. or its affiliates.

Copyright 2003, Solvay Solexis, Inc. All Rights Reserved.